

TSP 030 – Finixa adhesion primer 400ml for easy seam sealer

Description

High quality, fast drying plastic primer to treat surfaces, treated and untreated, of several types of plastic.

Product characteristics

Fast drying
Excellent adhesion
Re-sprayable with all lacquer systems

Physical and Chemical Characteristics

Contents : 400 ml
Base : Polyolefine resin
Colour : Transparent
VOC-content : Approximately 99% w/w
Solid content : Approximately 1% w/w
Coverage : 2 to 3 m²
Re-sprayable : After 10 to 15 minutes

Usage

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment

The surface should be clean, dry and free of grease. When desired, slightly sand the surface, grain 600.

Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the plastic primer in maximum two (2) thin layers. After drying, without sanding, re-sprayable with all lacquer systems.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds). The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for our own experimentation.

It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes.

This information may be subject to revision as new knowledge and experience becomes available.

Since we cannot anticipate all variations in actual end-use conditions, Chemicar make no warranties and assume no liability in connection with any use of this information.

This information does not constitute a specification and is only intended to show the typical properties of the product. Product safety information is available on request.

Data in this Technical Data Sheet relates only to the specific materials designated here in and not to use in combination with any other material or process.

The information given here is the best available at time of issue. It is based on our present knowledge but does not constitute a contractual description of product properties.