

Product Information

Wood adhesive system 3326

- General assembly glue

3326 is all-round glue that is developed to fit as many applications as possible. It provides good bonding to wood and even hard and difficult to glue wood species.

Product Specification

	3326	
Product	PVAc adhesive	
Delivery Form	Liquid	
Colour	White	
Viscosity (at time of production)	7000 - 14000 mPas (Brookfield RVT sp6, 20rpm at 25°C / 77°F)	
Dry Content	45 - 48%	
Density	App. 1080 kg/m ³	
pH (at time of production)	5,0 - 7,0 (at 25°C / 77°F)	
Storage Life (months)	20°C/68°F	30°C/86°F
	36	18
Storage Condition	<p>Recommended storage temperature 15-20°C. Only short term exposure to temperatures below 5°C or above 30°C is acceptable.</p> <p>Frozen and thawed product cannot be used due to irreversible changes in the product.</p> <p>During storage the glue will mature and the viscosity can increase.</p> <p>The product can form a skin on the surface if the container is not properly closed. The product shall always be stored in closed packaging.</p>	
Formaldehyde Info	Contains no formaldehyde, the system fulfils F****.	
Glue Line Properties	<p>Gives elastic glue lines. Light coloured glue lines.</p> <p>EN204 class D1</p>	
Approvals	This system is classified as F**** with the JAIA registration number 005449 (Japan Adhesives Industry Association).	
Discolouration	The product does not discolour the wood. However, iron which might come from the glue spreader can together with the tannic acids in some wood species, especially oak, give a discolouration.	

Contact Information

Stockholm, Sweden +46 8 743 40 00
High Point, USA +1 336 841 5111
Singapore +65 6762 2088
Medellin, Colombia +57 4 3618888
www.akzonobel.com/adhesives

Version: 06 (2016-04-29)

Reason for changes: Updates in Product Specification

Gluing Operation Information

Applications	Edge glued panels General assembly Others Solid wood lamination	
Press Type	Clamp Carrier Cold Press Continuous Press High Frequency Hot Press	
Glue line temperature	10 - 80°C	
Press Time, 20°C / 68°F (pine-pine, 65% RH, 150 g/m ² , 15 g/ft ²)	8'	
Press Time, 30°C / 86°F (pine-pine, 65% RH, 150 g/m ² , 15 g/ft ²)	--	
Pressure	0,1 - 1,0 MPa	
Assembly Time, 20°C / 68°F (pine-pine, 65% RH, 150 g/m ² , 15 g/ft ²)	Open: 8'	Closed: 10'
Assembly Time, 30°C / 86°F (pine-pine, 65% RH, 150 g/m ² , 15 g/ft ²)	Open: 4'	Closed: 5'
Glue Spread	Edge glued panels: 120 - 180 g/m ² General assembly: 90 - 300 g/m ² Others: 90 - 300 g/m ² Solid wood lamination: 150 - 250 g/m ²	
Moisture content of wood	5 - 15%, preferably 7 - 10%	
Preparation of wood	For best result the wood must be smoothly planed. For optimum bond strength the bonding operation shall take place within 24 hours after preparation.	
Temperature of wood	In order to meet the given press times the temperature of the wood must not be below 20°C / 68°F.	
Gluing of impregnated wood	Can in most cases be used but must be evaluated in each case.	
Post curing		

Contact Information

Stockholm, Sweden +46 8 743 40 00
High Point, USA +1 336 841 5111
Singapore +65 6762 2088
Medellin, Colombia +57 4 3618888
www.akzonobel.com/adhesives

Version: 06 (2016-04-29)

Reason for changes: Updates in Product Specification

Machinery

Applicator	Toothed trowel
	Brush
	Hand roller
Mixer	Not applicable
Accessories	Not applicable

Handling and HSE info

Handling	Always use gloves and goggles when handling the product.
Cleaning	Use lukewarm water for glue on skin and machinery. Cleaning should start before the system dries.
Waste handling - of the products	<p>Normally not to be considered as hazardous waste. Leave residues to dry before sending it off for disposal.</p> <p>For 2 component systems the hardener may be considered as hazardous waste, check the SDS (section 13).</p> <p>NOTE! There might be national and/or local regulatory differences, therefore always keep a dialogue with the local authorities.</p>
Waste water treatment - of the waste water	<p><u>Chemical precipitation → drain*</u></p> <p>Please contact Environmental Advisor at the Environmental Department for further information regarding chemical precipitation.</p> <p>* municipal sewage with biological treatment</p> <p>For more info, see General Information.</p> <p>NOTE! There might be national and/or local regulatory differences, therefore always keep a dialogue with the local authorities.</p>
Health and Safety	For more information, see respective SDS.

Legal clause

The information is based on laboratory tests and practical experience. It is introductory and intended to help the user find the most suitable method of working. Since the user's production conditions are beyond our control, we cannot be held responsible for the results of the work which is affected by local circumstances. In each particular case testing and continuous control are recommended.

Contact Information

Stockholm, Sweden +46 8 743 40 00
 High Point, USA +1 336 841 5111
 Singapore +65 6762 2088
 Medellin, Colombia +57 4 3618888
www.akzonobel.com/adhesives

Version: 06 (2016-04-29)

Reason for changes: Updates in Product Specification