

HALLEY UV200

1K UV PRIMER FILLER



TECHNICAL DATA SHEET **C43**

Version: 230109

DESCRIPTION

Polyester primer suitable for medium and small repairs, allowing drying times close to a minute with the use of UV drying lamps, significantly reducing repair process times.



PHYSICAL CHARACTERISTICS

Nature: Unsaturated polyester

Color: Translucent

Specific weight: 1,4kg/l a 20°C

VOC (Application Mix)	200 g/l
VOC USA (Application Mix)	14 g/l
Yield (Per coat)	9-13 m ² /l

SURFACE OR SUPPORT PREPARATION




Process	OEM paint	Cataphoresis	Polyester putties	Aluminium	Steel	Electro zinc plated steel	Galvanized steel	Plastics*
 P240 P320	•	•	•	•	•	•	•	•
 DA93	•	•	•	•	•	•	•	•

**In applications on plastics, once the support has been prepared and before using the primer, it is necessary to use the adhesion promoter for Primerplast plastics.*

MIXING RATIO

	Vol.	Weight
 Halley UV200	Ready for use. DO NOT add solvent thinner	
 F/4 a 20°C	25 s	


APPLICATION METHOD

Support	Metal	Plastic
	1.2-1.4 mm	1.2 mm
Hybrid		
	1.5-2.0 bar	1.5-2.0 bar
Total dry maximum thickness	120 µm	80 µm
	2	2 thin
20°C	2 min. between coats	2 min. between coats
Drying between coats	No	Yes*
20°C	5 minutes before final drying	2 minutes before final drying

*See drying chart for exposure time to UV light

When repairing with colors that have low covering power, to improve the result, apply one coat of the equivalent recommended primer color from the corresponding WB basecoat system.

DRYING

	Irradiance	Static curing time
	12-55 mW/cm ²	2 min.
	56-200 mW/cm ²	1 min.
	>200 mW/cm ²	30 s.

UV LED 395nm (20°C)

HALLEY UV200

1K UV PRIMER FILLER



TECHNICAL DATA SHEET **C43**

Version: 230109

DRYING

UV LED
395nm (20°C)

Curing in motion Static curing

Scangrip UV gun (Robled)

Lamp-support distance	10 cm	10 cm	56 cm
Irradiance	340 mW/cm ²	340 mW/cm ²	14 mW/cm ²
Illuminated diameter	18 cm	18 cm	68 cm
Drying time	1 min.	30 s.	2 min.

Drying time increases for: higher thicknesses than previously recommended, less powerful lamps and large surfaces where the lamp has to be moved away.

In case of thicknesses greater than those recommended above, start drying by placing the lamp at a greater distance and gradually move it closer.

To ensure curing of the edges and blurring of the patch/part, remove the masking paper during lamp drying.

Using lower intensity lamps in the dominant wavelength range (395nm) may increase drying time.

For curing in motion it is important not to have a repair surface larger than 50x50 cm; in case of larger dimensions increase the curing time.

SANDING

INITIAL	P320/P400
FINAL	P500/P600

EQUIPMENT CLEANING

Clean the spray gun and its components with cleaning solvent after application.

HALLEY UV200

1K UV PRIMER FILLER



TECHNICAL DATA SHEET **C43**

Version: 230109



SAFETY

Consult the product label. For more information consult the safety data sheets. Comply with occupational health and safety and waste disposal guidelines.

Wear protective goggles with 100% UV filter when handling the lit lamp and avoid contact of UV light with the skin.

STORAGE

The product hardens in contact with daylight, therefore it is necessary to keep the product container open for as short a time as possible. Do not leave the product for more than 5 days inside the opaque cups.

Keep in a cool and ventilated place avoiding exposure to direct sunlight. Store between 5°C and 30°C.

GUARANTEE

In original unopened packaging, one year from date of manufacture.

For any technical information, contact our Customer Support Service or our Technical Department

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO S.A.U reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

All clauses contained herein apply to any future changes or modifications.